



Technical data sheet #5

PLASTI DIP® /U.V. STABLE

(F-819, F-820 & F-698)

FOR INDUSTRIAL USE ONLY

DESCRIPTION:

PLASTI DIP® is an air dry, synthetic rubber coating that can be easily applied by spraying, brushing or dipping. PLASTI DIP® resists moisture, acids, abrasion, weathering, electrical shock, skidding/slipping, corrosion; coats and gives a comfortable, controlled, color coded grip to all types of tools; lawn and garden, mechanical, electrical, woodworking and masonry.

PLASTI DIP® can also be applied to:

Wood: seals and protects from weathering and prevents splinters.

Metal: reduces vibration, deadens sound, prevents corrosion, insulates electrically and from extreme temperatures.

Glass: shatterproofs glass objects (available in clear).

Rope/Fabrics: weatherproofs, prevents rotting and fraying.

Plastics: protects delicate surfaces from scratches.

Rubber: weatherproofs, wear resistant.

SPECIFICATIONS:

Solids: (wt.) 24%

Tensile: (ASTM D-638) 3,740psi

Elongation: (ASTM D-638) 430%

Cut resistance: (ASTM D-1044) very good

Coverage: 40 sq.ft. per gallon at 10 mils

Stone abrasion: (ASTM D-3170) excellent

Shelf life: 1+ years at 77°F unopened container

Viscosity range: 80 – 100 K.U. @ 77°F (+/- 2°F)

Weatherability: (ASTM G-53)

3-5 years: PLASTI DIP

7-10 years: PLASTI DIP U.V.

Chemical resistance:

acids, alkalines, pollutants: excellent

petroleums: limited

ALTERNATIVE PRODUCTS:

For a water base alternative see HCFeccs® technical data sheet

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

PLASTI DIP, HCF, Performix and logo are registered trademarks of PLASTI DIP INTERNATIONAL
BINKS is a registered trademark of BINKS MFG. CO., Franklin Park, IL

SURFACE PREPARATION

MIX WELL BEFORE USE.

All surfaces to be coated must be free of all oils, grease, dirt, wax and loose rust. A sandblasted or rough surface improves adhesion. Use PLASTI DIP® PRIMER on all metals for best results.

SPRAYING: Pressure pot may be used (siphon cup not recommended). Dilute with recommended thinners up to 50% as needed. Gently mix before spraying. Apply wet overlapping coats, holding gun 6"-12" from surface, using a 4"-6" pattern. Allow 10-20 minutes dry time before applying additional coats to desired thickness.

RECOMMENDED EQUIPMENT AND SETTINGS:

Binks® model 95 gun

Nozzle: 63B

Needle: 663A

Material: 20-25psi

Atomization: 15-25psi

Dilution: as needed

Cap: 63PB (up to 50% dilution) or 66SD (up to 50% dilution) for heavier build up.

Clean up: See recommended thinners.

SPRAYING: Airless equipment may be used. Use as described above.

Tip size: .011 - .019

Pressure: as needed

Dilution: up to 50%

DIPPING: Dilute with recommended thinners up to 25% as needed. Gently mix before each use. Do not introduce air bubbles. Insert item 1" every 5 seconds. Remove at same rate. Allow 30-40 minutes (dry to the touch) dry time before applying additional coats to desired thickness.

BRUSHING: Dilute with recommended thinners up to 25% as needed. Gently mix before each use. Apply wet overlapping coats using a soft natural bristle brush. Allow 10-20 minutes (dry to the touch) dry time before applying additional coats to desired thickness.

HINTS:

Recommended thinners: PLASTI DIP® THINNER, Toluene or VM&P Naphtha. A dry film thickness of 12-15 mils is recommended for best results. Approximate dry mil thickness per coat, dipping 6-8 mils; brushing 4-5 mils; spraying 2-5 mils. **Allow 4 hours dry time per coat before use.** Allow overnight drying whenever possible. When using a dip tank, allow 6" minimum from fluid surface to tank top to avoid "skinning over". Avoid excessive air movement, heat or humidity. Always use proper ventilation and protection.