



PDC® F-879's' eccs®
IMC/ PMC Vinyl Urethane Spray Coating
FOR INDUSTRIAL USE ONLY

DESCRIPTION:

F-879's' is a fast dry, high quality, water base coating for **IMC** [in mold coating- polyurethane molding process] or **PMC** [post mold coating] as a finish coat over an **IMC** or directly on other types of foam such as EVA, PVC, polystyrene or minicell.

Applications include athletic padding, medical pads, seating, automotive components, polypropylene buoys, polystyrene dock floatation blocks, etc.... F-879's' is also a high solids, very low V.O.C. material, which makes it an Emission Control Coating System, eccs®.

No other single component water base coating out performs F-879's'. Not only is performance superior, but formula and colorant quality and consistency are superior as well. Finally, a product you can rely on batch after batch. The durability, safety, low environmental impact, as well as cosmetic appearance, you expect. The service and quality you deserve.

OTHER FEATURES INCLUDE:

- Non-flammable, very safe
- Very low VOC's
- Technical support second to none.
- Unmatched strength, durability and dry time.

SPECIFICATIONS:

- | | |
|---|--|
| Solids (wt): 34 % | Tensile: (ASTM-D 412) 2330 psi |
| Temperature use range: 0°F to 120°F | Elongation: (ASTM-D 412) 470 % |
| Block resistant: 4hr @ 120°F | Shelf life: 1+ year at 77°F unopened container |
| Coverage: 120 sq. ft. per gal at 5 mils | Finish: gloss |
| Tear Resistance: (ASTM D1004) .156 | |

Chemical resistance: In House Test Results [ASTM D-1308]

Ketone:	poor	Aromatics:	fair	DOUBLE CHECK
Aliphatics:	good	Alcohols:	good	
Acids:	good	Glycol:	fair	

ALTERNATIVE PRODUCTS:

F-791's', F-823's', F-779's'.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

PDC and eccs are registered trademarks of PLASTI DIP INTERNATIONAL
Performix and logo are trademarks of PLASTI DIP INTERNATIONAL
BINKS is a registered trademark of BINKS MFG. CO., Franklin Park, IL

SURFACE PREPARATION:

All surfaces to be coated must be free of any oils, dust, mold release or loose foam particles.

USE ADEQUATE VENTILATION. GENTLY MIX BEFORE EACH USE.

SPRAYING:

IMC [in mold coating]: Make sure tool/ mold is clean and free of mold release unless release has been tested and approved for suitability. Spray apply light even coat making sure to cover all surfaces evenly and completely. Allow coating to tack before adding foam mixture. The use of heated tool/ molds, external heat and air movement is recommended to speed and ensure coating is tacky as quickly as possible. Allow adequate time for foam mixture to complete cycle and for coating to set up. Remove from tool/ mold carefully. Coated part should remove easily without damage to coating skin. If coating sticks to tool/ mold, allow for longer tack time or speed drying process. If difficulty persists, contact Technical Support for assistance.

PMC [post mold coating] or applied directly to other foams:

Tack coat: Apply light, overlapping coats, holding gun 12"-24" from surface, using an 8"-12" pattern. Allow adequate dry time before applying Finish coat.

Finish coat: Apply wet overlapping coats to desired film thickness. Multiple coats can be applied. Allow adequate dry time between coats or handling.

Pressure Pot recommendations:

Binks® model 2001/ 95 gun or equivalent

Nozzle: 66SS

Cap: 66SS

Needle: 565

Material: 20 psi

Atomization: 10-25 psi

Dilution: not recommended

Clean up: immediately with water – if allowed to dry, use Acetone or M.E.K.

Airless or air assisted airless equipment may be used. Dilution is not suggested. Gently mix before spraying. Apply wet, overlapping coats, holding gun 12"-24" from surface, using 6"-12" pattern. Allow to completely dry before recoating or turning item over.

Tip size: .011-.026

Pressure: as needed

Dilution: not recommended

Clean up: immediately with water – if allowed to dry, use Acetone or M.E.K.

HINTS:

A dry film thickness of 6-8 mils should be used on all items; 8-10 mils on high wear items. Allow at least an overnight dry before stacking or storing coated items unless you've accelerated drying with heat. After allowing to air dry for 30 minutes, a recommended heat for drying is 100°F-150°F with moving air. Always use proper ventilation and protection.